



<b>PRODUCT DATA SHEET</b>	Page: 1 of 2
	US Revision: 3
<b>RD-E DECK QUARTZ</b>	Date: 04/13/2021
	Supersedes: 05/15/2013
	<b>R11</b>

**DESCRIPTION OF THE PRODUCT**

Waterborne, acrylic polymer, high performance, single component coating; filled with an aggregate to produce a non-skid surface for the RD Coatings products.

**USES:** To be used as a non-skid coating for the RD Coatings systems or as a block filler.

- FEATURES:**
- VOC- 7g/L, single package, water-borne.
  - Contains no chromates, lead or strong solvents.
  - Impact and erosion resistant.
  - Resistant to the effects of long-term weathering, UV light, salt water and most environmental chemicals.
  - Thixotropic non-sag properties allowing applications in thick layers up to 20 mils.

- SUBSTRATES:**
- Concrete
  - CMU Block
  - Brick
  - Steel
  - Non-Skid coating over any RD Coatings product

**APPLICATION INSTRUCTIONS**

**PREPARATION OF THE SUBSTRATE:** The substrate has to be free of all loosely adhered rust, degreased, dry, and free of dust. Prepare substrates by pressurized water cleaning using 4,000-5,000 psi pressure equipment with a “zero” degree oscillating tip (SSPC SP-12, WJ4). Remove any remaining loose and non-adhering substrate prior to coating. Contact your local RD Coatings representative for detailed information.

RD-E DECK QUARTZ may be applied directly to prepared substrate or to surfaces primed or coated with any RD Coatings product.

- APPLICATION CONDITIONS:** Environmental Conditions (general requirements):
- The minimum air and substrate temperatures; 45°F for 24hours.
  - The maximum surface temperature; 130°F.
  - The maximum relative humidity: 90%.
  - Surface temperature must be at least 5°F above the Dew Point, with no threat of rain for 3hours.

Drying Times Temperature Re-Coat Interval:  
60°F (80%RH) 7 Hours  
80°F (80%RH) 5 Hours  
95°F (80%RH) 3 Hours

**Notes:** The above figures are for RD-E DECK QUARTZ applied @ 12 wet mils. These figures do not account for airflow; wind speeds of even 5mph will greatly reduce the dry time.

- APPLICATION MEANS:**
- In most cases this product is applied using a brush or roller.
  - It can also be spray applied using a conventional air assisted texture gun.



<b>PRODUCT DATA SHEET</b>	Page: 2 of 2
	US Revision: 3
<b>RD-E DECK QUARTZ</b>	Date: 04/13/2021
	Supersedes: 05/15/2013
	<b>R11</b>

DILUTION: Can dilute with water to reduce viscosity.

CLEANING OF TOOLS: Water

CONSUMPTION: Theoretical Coverage / 6 Gallon Container:  
• 950 sq. ft. @ 6 mils DFT

PARTICULARITIES: Mix before use.

#### TECHNICAL DATA

FINISH: Flat

COLORS: Gray

SOLIDS CONTENT: In Weight: 65-67%  
In Volume: 58-61%

FLASH POINT: Non-Flammable

DRYING TIME: To Touch: 3-6 hours  
To Recoat: 6-24 hours, depending on temperature and humidity.

PACKING: 5.5 Gallon Units

STORAGE STABILITY: 2 years minimum; provided the original container is sealed and has been stored in a controlled environment.

TEST DATA: Available upon request.

#### SAFETY DATA

The safety data sheet is available on request. (See RD-E DECK MSDS)

This Data is given for information only. Since the manufacturer is not able to check the correct application of the products, they cannot accept any responsibility for it. This technical data sheet replaces all previous editions.



<b>PRODUCT DATA SHEET</b>	Page: 3 of 2
	US Revision: 3
<b>RD-E DECK QUARTZ</b>	Date: 04/13/2021
	Supersedes: 05/15/2013
	<b>R11</b>

**RD Coatings USA** 167 Avon Street, Stratford, CT 06615 P: 203-380-9477 F: 203-380-9488 [www.rdcoatingsusa.com](http://www.rdcoatingsusa.com)